

TC-9033
Thermally Conductive Epoxy
Aluminum Filled, Two-Part, High Strength

HANDLING & CURING	
Filler	Aluminum
Mix Ratio by Weight, resin : hardener	1:1
Mixed Specific Gravity, gms/cc @25 °C	.85
Mixed Viscosity, cP @25 °C	Paste
Pot Life, 100 gm mass @25 °C, hrs	4.0
Recommended Cure, hr/ °F	2/200
Alternate Cure, hr/ °F	24-48/RT
CURED PROPERTIES	
Temperature Resistance, °C	-65/+204
CTE, in/in/°F x 10⁻⁶(°C)	33 (66)
Thermal Conductivity, Btu-in/hr-ft²-°F	9.0
Tensile Shear Strength, psi	2,500
Volume Resistivity, ohms-cm	1.0 x 10 ⁵
Dielectric Strength, volts-mil	80
Chemical Resistance	Excellent
Color	Grey

General Information

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Shelf Life

This product has a six months minimum shelf life after date of manufacture, unless otherwise specified, in original, unopened containers.

Note

The data contained in this technical data sheet are furnished for information only. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein. INCURE will not be liable for any indirect, special, incidental or consequential loss or damage arising from this INCURE product, regardless of the legal theory asserted. INCURE recommends that each user adequately test its proposed use and application before repetitive use, using this data as a guide.